



TRANSFER FILM FOR DTF PRINTING

TECHNICAL FEATURES

- Thickness: 75 microns
- Hot peel (or cold peel) with temperature range **from 130°C/265°F to 160°C/320°F***

Suitable for hot melt powder glues that melt starting from 110°C/230°F (recommended actual internal oven temperature: 140°C/285°F)

Matte/matte film with **matte printing finish**

No powder residue left on the film

For brighter colors and durability, a **second press** may be needed due to temperature and application time

* The technical info depends on the DTF printer settings, the glue and inks used.

INSTRUCTIONS

PRINT ON TRANSFER FILM

Mirror design

1

GLUE APPLICATION

Manually or with automatic shaker

2

OVEN CURING

Internal oven temperature up to 150°C/300°F*

3

HEAT PRESSING TRANSFER ON GARMENT

Temperature range from 130°C/265°F to 160°C/320°F*

4

LINER REMOVAL

Hot and semi-hot, depending on temperature and application time used*

5



Compliant with **REACH**
Regulation n°1907/2006/EU

STANDARD SIZES AVAILABLE

ROLLS

- h 30 cm x 100 mt / 12" x 328 ft
- h 40 cm x 100 mt / 16" x 328 ft
- h 60 cm x 100 mt / 24" x 328 ft
- h 80 cm x 100 mt / 31" x 328 ft
- h 120 cm x 100 mt / 47" x 328 ft

SHEETS

- A3 / 11,7" x 16,5"
- A4 / 8,3" x 11,7"
- cm 40x50 / 15,7" x 19,7"



CUSTOM SIZES

available on demand




Problems during the printing stage?

The DTF world is new and has a lot of variables to consider. You may have issues at first without really understanding why.

Don't give up, call us for help!

Our experience is at your disposal. We will work through the problem together, so you'll understand how to solve the issue and get the perfect application!



SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information abovementioned in this page. Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications.

Rev_2025/04

HEADQUARTERS B-FLEX ITALIA S.R.L. info@b-flexitalia.com | www.b-flexitalia.com
NORTH AMERICA BRANCH B-FLEX AMERICA LLC info@b-flexamerica.com | www.b-flexamerica.com
ASIA-PACIFIC BRANCH B-FLEX PACIFIC PTY LTD info@b-flexpacific.com | www.b-flexpacific.com

follow us

